

Technical Data Sheet

HDPE 0.50 mm Black Smooth

PROPERTY	TEST METHOD	FREQUENCY (1)	UNIT Metric	1050921
SPECIFICATIONS				
Thickness (min. avg.) Thickness (min.)	ASTM D5199 ASTM D5199	Every roll Every roll	mm mm	0.50 0.45
Resin Density Melt Index - 190/2.16 (max.)	ASTM D1505 ASTM D1238	1/Batch 1/Batch	g/cc g/10 min	>0.932 1.0
Sheet Density Carbon Black Content Carbon Black Dispersion OIT - standard (avg.)	ASTM D792 ASTM D4218 ASTM D5596 ASTM D3895	Every 10 rolls Every 2 rolls Every 10 rolls 1/Batch	g/cc % Category min	≥0.940 2.0 - 3.0 Cat. 1 / Cat. 2 100
Tensile Properties (min. avg) (2) Strength at Yield Elongation at Yield Strength at Break Elongation at Break	ASTM D6693	Every 2 rolls	kN/m % kN/m %	7 12 13 650
Tear Resistance (min. avg.) Puncture Resistance (min. avg.)	ASTM D1004 ASTM D4833	Every 5 rolls Every 5 rolls	N N	58 178
Dimensional Stability Stress Crack Resistance (SP-NCTL) Oven Aging - % retained after 90 days	ASTM D1204 ASTM D5397 ASTM D5721	Certified 1/Batch Per formulation	% hr	±2 500
HP OIT (min. avg.) UV Res % retained after 1600 hr	ASTM D5885 ASTM D7238	Per formulation	%	80
HP-OIT (min. avg.) Low Temperature Brittleness	ASTM D5885 ASTM D746	Certified	% °C	50 - 77
SUPPLY SPECIFICATIONS(Roll dir	mensions may vary ±19	%)		
Roll Dimension - Width	-		m	8.00
Roll Dimension - Length	-		m	420.0
Area (Surface/Roll)	-		m²	3360.0

NOTES

- 1. Testing frequency based on standard roll dimensions and one batch is approximately 180,000 lbs (or one railcar).
- 2. Machine Direction (MD) and Cross Machine Direction (XMD or TD) average values should be on the basis of 5 specimens each direction.
- * All values are nominal test results, except when specified as minimum or maximum.
- * The information contained herein is provided for reference purposes only and is not intended as a warranty of guarantee. Final determination of suitability for use contemplated is the sole responsibility of the user. SOLMAX assumes no liability in connection with the use of this information.

Solmax is not a design professional and has not performed any design services to determine if Solmax's goods comply with any project plans or specifications, or with the application or use of Solmax's goods to any particular system, project, purpose, installation or specification.

